

Product Data Sheet


GRM PEEK

Benefits:

Excellent chemical resistance
Very low moisture absorption
Inherently good wear and abrasion resistance
Unaffected by continuous exposure to hot water or steam
Good resistance to gamma radiation

Design Data:

Polyether ether ketone
Available in sheet, rod & extruded shapes
Multiple grades, reinforcing compounds available



Typical Specifications:

Properties	Test Method	Typical Result
Hardness (Rockwell)	ASTM D-785	M100
Specific Gravity	ASTM D-792	1.31
Compressive Strength	ASTM D-695	20,000 psi
Tensile Strength	ASTM D-638	16,000 psi Min.
Temperature Range		+480°F Max.

www.grmcp.com

(936) 441-5910

11133 I-45 S. Suite Q
Conroe, TX 77302



Request a quote:

sales@grmcp.com

Design or specification help:

eng@grmcp.com